

A = Excellent

B = Good Minor, Effect, slight corrosion or discoloration.

C = Fair Moderate//Effect, not recommended for continuous use. Softening, loss of strength, swelling may occur.

D = Severe Effect, not recommended for ANY use.

No.	English Name	Chinese Name	接液部材質 Material of Wetted Body			主隔膜材質 Material of Main Diaphragm			推薦規格 Recommended Specifications
			鋁 (AL)	不銹鋼 (SUS316)	聚丙烯 (PP)	超高分子聚乙烯 (UPE)	鐵氟龍 (Teflon)	熱塑性橡膠 (Santoprene)	
1	Carbon monoxide	一氧化碳	A	A	A		A	A	DSXX-AAX-OXXX-XX
2	Chloroacetic Acid (Monochloroacetic Acid)	一氯乙酸		C	A	A	A 20°C	C	DSXX-PXX-TPTP-XX
3	Dipropylene glycol	一縮二丙二醇			A		A		DSXX-PXX-TPTP-XX
4	Ethylene diamine	乙二胺	C	A	A	A	A	A	DSXX-PXX-TPTP-XX
5	Ethanedioic acid (Oxalic acid)	乙二酸(草酸)	B	B	A	A	A	A	DSXX-PXX-TPTP-XX
6	Ethyl oxalate	乙二酸二乙酯 (草酸二乙酯)	B	B	A	A	A	B	DSXX-PXX-TPTP-XX
7	Ethylene glycol	乙二醇	A	A	A	A	A 20°C	A	DSXX-AAX-UEXS-XX
8	Glycol methylene ether	乙二醇二甲醚	A	A	A	A	A	A	DSXX-AAX-UEXS-XX
9	Cellosolve® (Glycol Ethers)	乙二醇單乙醚	A	A	A		A	D	DSXX-AAX-TAXS-XX
10	Butyl glycol	乙二醇單丁醚			A			A	DSXX-PXX-OTPT-XX
11	Acetylene (Ethyne)	乙炔	A	A	D		A	C	DSXX-AAX-TAXS-XX
12	Ethylbenzol (Ethylbenzene)	乙苯		A	C	A	A	C	DSXX-SAX-TXTS-XX
13	Carbitol	二甘醇單乙醚	B	A			A	B	DSXX-SAX-TXTS-XX
14	Ethyl Amine (Monoethylamine)	乙胺	B	B			A		DSXX-AAX-TAXS-XX
15	Ethyl group	乙基						C	
16	Ethyl diglycol	乙基二甘醇				A			
17	Ethylhexyl Alcohol (Ethylhexanol)	乙基己醇	A	A			A		DSXX-AAX-TAXS-XX
18	Ethyl pentachlorobenzene	乙基五氯苯					A		
19	Ethyl chloride	乙基氯		A	C	A	A	C	DSXX-SAX-TXTS-XX
20	Ethyl chloride (dry)	乙基氯 (乾)	B	A		A	A		DSXX-SAX-TXTS-XX
21	Ethyl chloride (wet)	乙基氯 (濕)	D	C		A	A		DSXX-SAX-TXTS-XX
22	Ethyl cellulose	乙基纖維素	B	B	C		A	A	DSXX-AAX-TXTS-XX
23	Ethylene (Ethene)	乙烯	A	A			A	C	DSXX-AAX-TAXS-XX
24	Vinyl cyanide	乙烯基氯			A				DSXX-PXX-TPTP-XX
25	Vinyl bromide	乙烯基溴			A				DSXX-PXX-TPTP-XX
26	Ethenechlorohydrine	乙烯氯醇					A		
27	Ethane	乙烷		A	A		A	C	DSXX-PXX-TPTP-XX
28	Ethanethiol	乙烷硫醇	B	B			A	C	DSXX-SAX-TXTS-XX
29	Ethane nitrile	乙烷腈					A		

A = Excellent

B = Good Minor, Effect, slight corrosion or discoloration.

C = Fair Moderate/Effect, not recommended for continuous use. Softening, loss of strength, swelling may occur.

D = Severe Effect, not recommended for ANY use.

No.	English Name	Chinese Name	接液部材質 Material of Wetted Body			主隔膜材質 Material of Main Diaphragm			推薦規格 Recommended Specifications
			鋁 (AL)	不銹鋼 (SUS316)	聚丙烯 (PP)	超高分子聚乙烯 (UPE)	鐵氟龍 (Teflon)	熱塑性橡膠 (Santoprene)	
30	Ethyl Mercaptan (Ethanethiol)	乙硫醇	A	A		A	A		DSXX-AAX-UEXS-XX
31	Acetonitrile (Methylcyanide)	乙腈 (甲基氰、氰甲烷)	A	A		A	A 60°C	A	DSXX-AAX-UEXS-XX
32	Acetophenone	乙酰苯		B		A	A	B	DSXX-SAX-USXS-XX
33	Acetamide	乙酰胺	A	D	A	A	A	A	DSXX-AAX-UEXS-XX
34	Ethanoic acid (Acetic acid)	乙酸	C	A	A	A	A		DSXX-PXX-TPTP-XX
35	Acetic acid 25%	乙酸 25%	A	A	A		A	B	DSXX-AAX-TAXS-XX
36	Acetic acid 30%	乙酸 30%	B	A	A		A	B	DSXX-PXX-OPTP-XX
37	Acetic acid 50%	乙酸 50%	D	A	B		A	B	DSXX-PXX-OPTP-XX
38	Acetic acid 60%	乙酸 60%	D	A	B	A	A		DSXX-PXX-TPTP-XX
39	Acetic acid, glacial	乙酸·冰的	C	A	A		A	B	DSXX-PXX-TPTP-XX
40	Acetic acid, vapor	乙酸·蒸氣	D	B	C		A		DSXX-SAX-TSXS-XX
41	Vinyl acetate	乙酸乙烯酯	B	A			A		DSXX-SAX-TSXS-XX
42	Ethyl Acetoacetate (Acetoacetic Ester)	乙酸乙酯(醋酸乙酯)	A	A		A	A	D	DSXX-AAX-UEXS-XX
43	Pentyl acetate	乙酸戊酯(香蕉油)	B	A	C		A	B	DSXX-SAX-TSXS-XX
44	Butyl acetate	乙酸正丁酯	A	A	C	A	A	B	DSXX-AAX-UAXX-XX
45	n-Propyl acetate	乙酸正丙酯	A	A	D		A	B	DSXX-AAX-TAXS-XX
46	Amyl acetate	乙酸正戊酯	C	A	A	A	A 60°C	B	DSXX-SAX-TSTS-XX
47	Methyl acetate (Methyl ethanoate)	乙酸甲酯	A	B	A	A	A	B	DSXX-AAX-UAXX-XX
48	Octyl acetate	乙酸辛酯	A	A			A		DSXX-AAX-TAXS-XX
49	Acetic anhydride	乙酸酐	A	B	A	A	A	A	DSXX-PXX-OPTP-XX
50	Isobutyl acetate	乙酸異丁酯	A			A 20°C	A 20°C		DSXX-AAX-UEXS-XX
51	Isopropyl acetate	乙酸異丙酯	A		B		A	B	DSXX-AAX-TAXS-XX
52	Isoamyl acetate	乙酸異戊酯	A	A			A		DSXX-AAX-TAXS-XX
53	Sodium acetate	乙酸鈉	A	B		A	A	A	DSXX-AAX-UEXS-XX
54	Calcium acetate	乙酸鈣	A			A	A		DSXX-AAX-UEXS-XX
55	Potassium acetate	乙酸鉀			A	A	A	A	DSXX-PXX-TPTP-XX
56	Copper acetate	乙酸銅			A	A	A		DSXX-PXX-TPTP-XX
57	Ammonium acetate	乙酸銨		A		A			DSXX-SAX-USXS-XX
58	Aluminium acetate, aqueous	乙酸鋁·含水		B	A	A		A	DSXX-PXX-OPTP-XX

A = Excellent

B = Good Minor, Effect, slight corrosion or discoloration.

C = Fair Moderate/Effect, not recommended for continuous use. Softening, loss of strength, swelling may occur.

D = Severe Effect, not recommended for ANY use.

No.	English Name	Chinese Name	接液部材質 Material of Wetted Body			主隔膜材質 Material of Main Diaphragm			推薦規格 Recommended Specifications
			鋁 (AL)	不銹鋼 (SUS316)	聚丙烯 (PP)	超高分子聚乙烯 (UPE)	鐵氟龍 (Teflon)	熱塑性橡膠 (Santoprene)	
59	Zinc acetate, aqueous	乙酸鋅 · 含水	A	A	A	A	A	A	DSXX-AAX-UEXS-XX
60	Cellulose acetate	乙酸纖維素			A		A		DSXX-PXX-TPTP-XX
61	Ethyl Alcohol (Ethanol)	乙醇	A	A	A	A	A 100°C	A	DSXX-PXX-TPTP-XX
62	Monoethanolamine	乙醇胺	B	A	D		A 20°C	A	DSXX-AAX-TAXS-XX
63	Ethanol dicarboxylic acid	乙醇羧酸					A		
64	Ethaneamide	乙醇酰胺					A		
65	Glycolic acid	乙醇酸		B	A	A	A 20°C	A	DSXX-PXX-TPTP-XX
66	Butyl glycolate	乙醇酸丁酯				A 40%			
67	Ethyl ether	乙醚	B	A	C	A	A	D	DSXX-SAX-TSXS-XX
68	Acetaldehyde (Ethanal)	乙醛	A	A	A	A	A	B	DSXX-AAX-UEXS-XX
69	Methyl acetoacetate	乙醯乙酸甲酯		A		A	A		DSXX-SAX-TSXS-XX
70	Acetyl acetone	乙醯丙酮	D	B			A	B	DSXX-SAX-TSXS-XX
71	Acetanilide	乙醯苯胺		B			A		DSXX-SAX-TSXS-XX
72	Acetyl chloride	乙醯氯	D	B	D	A	A	B	DSXX-SAX-TSXS-XX
73	Butanediol	丁二醇		A		A	A		DSXX-SAX-TSXS-XX
74	Ethyl glycol acetate	丁氧基乙酸乙酯				A			
75	Butyl diglycol acetate	丁基二甘醇乙酸酯				A			
76	Butene (Butylene)	丁烯	A	A			A	D	DSXX-AAX-TAXS-XX
77	Butylene glycol	丁烯甘醇		A		A			
78	Butane - gas	丁烷 - 氣體	A	A	C		A	D	DSXX-AAX-TAXS-XX
79	Butane - wet	丁烷 - 濕	A	A	A				DSXX-PXX-TPTP-XX
80	Methyl Ethyl Ketone (Butanone)	丁酮	A	A	D	A	A	B	DSXX-AAX-UEXS-XX
81	Butyric acid (aqueous)	丁酸 (含水)	A	B	A	A	A	A	DSXX-AAX-UEXS-XX
82	Ethyl butyrate	丁酸乙酯	B	A	B		A		DSXX-SAX-TSTS-XX
83	n-Butyl butyrate	丁酸丁酯	A	A			A		DSXX-AAX-TAXS-XX
84	Isobutyl n-Butyrate(isobutyl butyrate)	丁酸異丁酯					A		
85	Isoamyl butyrate	丁酸異戊酯	A	A			A		DSXX-AAX-TAXS-XX
86	Butadiene	丁二烯		A	C		A	C	DSXX-SAX-TSTS-XX
87	Butyl alcohol (Butanol)	丁醇	A	A	A	A	A	A	DSXX-AAX-UEXS-XX

A = Excellent

B = Good Minor, Effect, slight corrosion or discoloration.

C = Fair Moderate/Effect, not recommended for continuous use. Softening, loss of strength, swelling may occur.

D = Severe Effect, not recommended for ANY use.

No.	English Name	Chinese Name	接液部材質 Material of Wetted Body			主隔膜材質 Material of Main Diaphragm			推薦規格 Recommended Specifications
			鋁 (AL)	不銹鋼 (SUS316)	聚丙烯 (PP)	超高分子聚乙烯 (UPE)	鐵氟龍 (Teflon)	熱塑性橡膠 (Santoprene)	
88	Butyraldehyde	丁醛	A	A		A	A	C	DSXX-AAX-UEXS-XX
89	Carbitol acetate	二乙二醇乙醚醋酸酯						B	
90	Butyl carbitol	二乙二醇丁醚	A				A		DSXX-AAX-TAXS-XX
91	Diethylene glycol dimethyl ether	二乙二醇二甲醚				A			
92	Diethylamine	二乙胺			B	A	A		DSXX-PXX-TPTP-XX
93	Diethylbenzol	二乙基苯			-			C	
94	Diethyl ketone	二乙基酮				A			
95	Diethanolamine	二乙醇胺	A			A	A		DSXX-AAX-UEXS-XX
96	Dibutylamine	二丁胺			B		A	B	DSXX-PXX-TPTP-XX
97	Butyl ether (Dibutyl ether)	二丁醚	A	A	D	A	A		DSXX-AAX-UEXS-XX
98	Diethylene glycol (Diglycol)	二甘醇			A	A	A		DSXX-PXX-TPTP-XX
99	Xylene (Xylol) (Dimethyl benzene)	二甲苯	A	B	D		A	C	DSXX-AAX-TAXS-XX
100	Xylidine mixtures	二甲苯胺混合物	B				A	C	DSXX-AAX-TAXS-XX
101	Xylenol	二甲苯酚			B		A		DSXX-PXX-TPTP-XX
102	Dimethylamine	二甲胺		A		A	A		DSXX-SAX-TSTS-XX
103	Dimethyl formamide	二甲基甲醯胺			A	A 60°C	A	A	DSXX-PXX-TPTP-XX
104	Dimethyl furane	二甲基呋喃				A			
105	Dimethylaniline	二甲基苯胺				A	A	B	
106	Dimethyl sulfide	二甲硫醚	A	A			A		DSXX-AAX-TAXS-XX
107	Dimethyl ether	二甲醚	B	B		A	A		DSXX-AAX-UEXS-XX
108	Digallic acid	二沒食子酸					A		
109	Dibenzyl ether	二苄醚	B	B		A	A	C	DSXX-AAX-UEXS-XX
110	Diethylene triamine	二亞乙基三胺	A	A			A		DSXX-AAX-TAXS-XX
111	Diphenyl Oxides (Phenyl Ether)	二苯醚	B	A			A	C	DSXX-AAX-UEXS-XX
112	Dioxysuccinic acid	二氧丁二酸					A		
113	Silicon dioxide	二氧化矽		A			A		DSXX-SAX-TSXS-XX
114	Sulfur dioxide	二氧化硫	A		B	A	A 20°C	D	DSXX-AAX-UEXS-XX
115	Sulfur dioxide 1%at 38°C	二氧化硫 1%於38°C	A	A	A		A	A	DSXX-AAX-UEXS-XX
116	Chlorine dioxide (dry)	二氧化氯 (乾)		A	C		A		DSXX-SAX-TSXS-XX
117	Chlorine dioxide (wet)	二氧化氯 (濕)	D	C	C		A		

A = Excellent

B = Good Minor, Effect, slight corrosion or discoloration.

C = Fair Moderate/Effect, not recommended for continuous use. Softening, loss of strength, swelling may occur.

D = Severe Effect, not recommended for ANY use.

No.	English Name	Chinese Name	接液部材質 Material of Wetted Body			主隔膜材質 Material of Main Diaphragm			推薦規格 Recommended Specifications
			鋁 (AL)	不銹鋼 (SUS316)	聚丙烯 (PP)	超高分子聚乙烯 (UPE)	鐵氟龍 (Teflon)	熱塑性橡膠 (Santoprene)	
118	Carbon dioxide	二氧化碳	A	A	A		A	A	DSXX-AAX-OXXX-XX
119	Dioxolane	二氧戊環					A	C	
120	Diisopropyl ketone	二異丙[基]酮					A	C	
121	Diisopropanolamine	二異丙醇胺						C	
122	Carbon disulfide	二硫化碳	C	A	D	A	A 60°C	D	DSXX-SAX-TSXS-XX
123	Dichloroethene	二氯乙烯		A			A	D	DSXX-SAX-TSXS-XX
124	Ethylene dichloride (Dichloroethane)-dry	二氯乙烷 (乾)	A	A		A	A	D	DSXX-SAX-TSXS-XX
125	Ethylene dichloride (Dichloroethane)-wet	二氯乙烷 (濕)	D	B	D		A	D	DSXX-SAX-TSXS-XX
126	Dichloroacetic acid	二氯乙酸				A			
127	Dichlorobutane	二氯丁烷		A			A		DSXX-SAX-TSXS-XX
128	DDT	二氯二苯三氯乙		A					DSXX-SAX-TSXS-XX
129	DDT and Deodorized Kerosine	二氯二苯三氯乙和 除臭的煤油		A			A		DSXX-SAX-TSXS-XX
130	Benzylidene chloride	二氯化苄				A			
131	Sulfur dichloride	二氯化硫					A		
132	Dichloropropane (Propene dichloride)- dry	二氯丙烷 (乾)		A			A		
133	Dichloropropane (Propene dichloride)- wet	二氯丙烷 (濕)		C			A		
134	Methyl dichloride	二氯甲烷	D		D		A	D	
135	Dichlorophenol	二氯苯酚		B					DSXX-SAX-TSXS-XX
136	Dinitrotoluene	二硝基甲苯		A			A	B	DSXX-SAX-TSXS-XX
137	Ethylene Dibromide (Ethylene Bromide)	二溴乙烷	D	B	D		A		DSXX-SAX-TSXS-XX
138	Methylene bromide	二溴甲烷	D	A			A		DSXX-SAX-TSXS-XX
139	Dicarboxylic acid	二羧酸					A		
140	Dioxane	二噁烷	A		A	A	A		DSXX-AAX-UEXS-XX
141	Dicyclohexylamine	二環己胺					A	B	
142	Margarine	人造黃油	A	A	B	A	A	B	DSXX-AAX-TAXS-XX
143	Octane	辛烷			D		A	B	
144	Dodecyl benzene	十二烷基苯	A	A			A		DSXX-AAX-TAXS-XX

A = Excellent

B = Good Minor, Effect, slight corrosion or discoloration.

C = Fair Moderate/Effect, not recommended for continuous use. Softening, loss of strength, swelling may occur.

D = Severe Effect, not recommended for ANY use.

No.	English Name	Chinese Name	接液部材質 Material of Wetted Body			主隔膜材質 Material of Main Diaphragm			推薦規格 Recommended Specifications
			鋁 (AL)	不銹鋼 (SUS316)	聚丙烯 (PP)	超高分子聚乙烯 (UPE)	鐵氟龍 (Teflon)	熱塑性橡膠 (Santoprene)	
145	Dodecyl alcohol	十二醇					A		
146	Oleic acid	十八烯酸	A	B	B		A		DSXX-AAX-TAXS-XX
147	Octadecanoic acid	十八碳烷酸				A	A	B	
148	Tricresyl Alcohol (Tridecanol)	十三烷醇					A		
149	Hexadecanoic acid	棕櫚酸	B	B	A	A	A	B	DSXX-SAX-TSXS-XX
150	Decahydronaphthalene (Decalin®)	十氫化萘			B	A	A		DSXX-PXX-TPTP-XX
151	Triethylamine	三乙基氨		A		A	A	D	DSXX-SAX-USXS-XX
152	Triethyl borane	三乙基硼烷					A	B	
153	Triethyl cellulose	三乙基纖維素					A		
154	Triethanolamine	三乙醇胺	A		A	A 20°C	A	A	DSXX-AAX-UETE-XX
155	Triethylene glycol	三甘醇			A	A	A		DSXX-PXX-TPTP-XX
156	Trimethylamine	三甲胺				A			
157	Isooctane	三甲基戊烷	A		A	A	A		DSXX-AAX-UEXS-XX
158	Chromic fluoride	三氟化鉻		C					
159	Sulfur trioxide	三氧化硫	A		A		A 20°C	C	DSXX-AAX-TAXS-XX
160	Sulfur trioxide, dry	三氧化硫 · 乾燥		A			A		DSXX-SAX-TSXS-XX
161	Trichloroethylene (dry)	三氯乙烯 (乾)	D	A	D		A	D	DSXX-SAX-TSXS-XX
162	Trichloroethylene (wet)	三氯乙烯 (濕)		C					
163	Ethylene Trichloride (Trichloroethene)	三氯乙烯(100%)	D	A	D		A	D	DSXX-SAX-TSXS-XX
164	Ethylene Trichloride (Trichloroethene)	三氯乙烯(40%)	D	A	A(20°C)		A	D	DSXX-SAX-TSXS-XX
165	Trichloroethane	三氯乙烷			A	A	A	D	DSXX-PXX-TPTP-XX
166	Trichloroethane (dry)	三氯乙烷 (乾)	D	A	D		A	D	DSXX-SAX-TSXS-XX
167	Trichloroethane (wet)	三氯乙烷 (濕)		C			A		
168	Trichloroacetic acid - 10%	三氯乙酸 - 10%	D	D	A	A	A	B	DSXX-PXX-TPTP-XX
169	Arsenic trichloride	三氯化砷						B	
170	Boron trichloride (dry)	三氯化硼 (乾)		B					
171	Boron trichloride (wet)	三氯化硼 (濕)		C					
172	Antimony chloride 50%	三氯化銻					A		
173	Phosphorus trichloride	三氯化磷	C	A	D	A	A	B	DSXX-SAX-USXS-XX
174	Phosphoric trichloride acid	三氯化磷酸					A		

A = Excellent

B = Good Minor, Effect, slight corrosion or discoloration.

C = Fair Moderate/Effect, not recommended for continuous use. Softening, loss of strength, swelling may occur.

D = Severe Effect, not recommended for ANY use.

No.	English Name	Chinese Name	接液部材質 Material of Wetted Body			主隔膜材質 Material of Main Diaphragm			推薦規格 Recommended Specifications
			鋁 (AL)	不銹鋼 (SUS316)	聚丙烯 (PP)	超高分子聚乙烯 (UPE)	鐵氟龍 (Teflon)	熱塑性橡膠 (Santoprene)	
175	Trichloropropane	三氯丙烷	D	A	D		A	D	DSXX-SAX-TSXS-XX
176	Chloroform	三氯甲烷	A		C	A	A		DSXX-AAX-UEXS-XX
177	Chloroform (dry)	三氯甲烷 (乾)		A		A	A	D	DSXX-SAX-TSXS-XX
178	Chloroform (wet)	三氯甲烷 (濕)		C		A	A	D	
179	Trichlorobenzene	三氯苯	D	A			A		DSXX-SAX-TSXS-XX
180	Trinitrotoluene (TNT)	三硝基甲苯					A	A	
181	Trihydroxyethylamine	三羥乙胺					A		
182	Vaseline	凡士林		A	A	A	A		DSXX-PXX-TPTP-XX
183	Soybean oil	大豆油	B	A	A		A	A	DSXX-PXX-OTPT-XX
184	Sodium bicarbonate	小蘇打		A	A		A	A	DSXX-PXX-TPTP-XX
185	Hexamethylene diamine	己二胺					A 20°C		
186	Diisooctyl adipate	己二酸二辛酯	A	A			A	C	DSXX-AAX-TAXS-XX
187	Hexylene glycol	己二醇	A				A		DSXX-AAX-TAXS-XX
188	Hexaline	己胺					A		
189	n-Hexene	己烯					A		
190	Hexane - 100%	己烷 - 100%			B	A	A	A / C	DSXX-PXX-TPTP-XX
191	Methyl butyl ketone	己酮	A		A		A		DSXX-AAX-TAXS-XX
192	Ketohexamethylene	己酮六亞甲基					A		
193	Caproic acid	己酸				A			
194	Hexanol	己醇	A		A	A	A		DSXX-AAX-UEXS-XX
195	Hexaldehyde	己醛	A				A	C	DSXX-AAX-UEXS-XX
196	Antifreeze	不凍液	A		A		A		DSXX-PXX-TPTP-XX
197	Tanning Liquors	丹寧酸	A	A			A	A	DSXX-AAX-TAXS-XX
198	Gallic acid	五倍子酸			A		A	B	DSXX-PXX-TPTP-XX
199	Pentachlorophenol	五氯苯酚	A	A			A		DSXX-SAX-TAXS
200	Lactam	內酰胺					A		
201	Hexahydropyridine	六氫吡啶；哌啶					A		
202	Hexachloroethane (dry)	六氯乙烷 (乾)		A					
203	Hexachloroethane (wet)	六氯乙烷 (濕)		C					

A = Excellent B = Good Minor, Effect, slight corrosion or discoloration. C = Fair Moderate/Effect, not recommended for continuous use. Softening, loss of strength, swelling may occur. D = Severe Effect, not recommended for ANY use.									
No.	English Name	Chinese Name	接液部材質 Material of Wetted Body			主隔膜材質 Material of Main Diaphragm			推薦規格 Recommended Specifications
			鋁 (AL)	不銹鋼 (SUS316)	聚丙烯 (PP)	超高分子聚乙烯 (UPE)	鐵氟龍 (Teflon)	熱塑性橡膠 (Santoprene)	
204	Nonane	壬烷					A		
205	Dibutyl ketone	壬酮				A			
206	Natural gas	天然氣	A	A	A		A		DSXX-AAX-TAXS-XX
207	Wood oil	木油		A			A		DSXX-SAX-TSXS-XX
208	Wood spirit	木精	A	A	C	A	A	A	DSXX-AAX-OXXX-XX
209	Water, fresh, tap	水・未煮沸		A			A		DSXX-SAX-TSXS-XX
210	Water, oil containing, brackish	水・含油・微鹹		A	A	A	A 20°C		DSXX-PXX-TPTP-XX
211	Water, distilled	水・蒸餾		A		A	A 20°C	A	DSXX-SAX-TSXS-XX
212	Water, acidic	水・酸性	C	A	A	A	A		DSXX-PXX-TPTP-XX
213	Water, mineral	水・礦物	B	C		A	A 20°C		DSXX-AAX-TAXS-XX
214	Water-methanol, mixed	水甲醇・混合	B	A	A		A		DSXX-PXX-TPTP-XX
215	Methyl Salicylate (Betula Oil)	水楊酸甲酯	A				A	B	DSXX-AAX-TAXS-XX
216	Salicylic aldehyde	水楊醛					A 20°C		
217	Milk	牛奶	A	A	A		A 20°C	A	DSXX-SAX-TSXS-XX
218	Aqua Regia	王水	D	D	C		A 60°C	D	DSXX-PXX-TPTP-XX
219	Dimethyl malonate	丙二酸二甲酯				A			
220	Propylene glycol	丙二醇	C	B	A	A	A	A	DSXX-PXX-TPTP-XX
221	Monomethyl ether	丙二醇甲醚					A	C	
222	Methyl glycol acetate	丙二醇甲醚乙酸酯				A			
223	Glycerol	丙三醇		A			A 20°C	A	DSXX-SAX-TSXS-XX
224	Glycerin (Propane triol)	丙三醇(甘油)	A	A	A	A	A	A	DSXX-AAX-UEXS-XX
225	Propyne	丙炔					A		
226	Propylamine	丙胺				A			
227	Propylene	丙烯	A	A			A	B	DSXX-AAX-TAXS-XX
228	Acrylonitrile	丙烯腈	C	A	B	A	A	B	DSXX-PXX-TPTP-XX
229	Acrylic acid	丙烯酸		B			A	A	DSXX-SAX-TSXS-XX
230	Ethyl acrylate	丙烯酸乙酯	A	A		A	A	C	DSXX-AAX-UEXS-XX
231	Butyl acrylate	丙烯酸丁酯				A		C	
232	Methyl acrylate	丙烯酸甲酯		A		A	A	B	DSXX-SAX-USXS-XX
233	Acrylates	丙烯酸鹽		C					

A = Excellent

B = Good Minor, Effect, slight corrosion or discoloration.

C = Fair Moderate/Effect, not recommended for continuous use. Softening, loss of strength, swelling may occur.

D = Severe Effect, not recommended for ANY use.

No.	English Name	Chinese Name	接液部材質 Material of Wetted Body			主隔膜材質 Material of Main Diaphragm			推薦規格 Recommended Specifications
			鋁 (AL)	不銹鋼 (SUS316)	聚丙烯 (PP)	超高分子聚乙烯 (UPE)	鐵氟龍 (Teflon)	熱塑性橡膠 (Santoprene)	
234	Acroleine	丙烯醛				A	A		
235	Propane	丙烷		A	A		A	C	DSXX-PXX-TPTP-XX
236	Propane diol	丙烷二醇				A			
237	Propionitrile	丙腈					A		
238	Dimethyl ketone (Acetone)	丙酮	A	A		A	A	B	DSXX-AAX-UEXS-XX
239	Acetocyanohydrine	丙酮氰醇			A			A	DSXX-PXX-OPTP-XX
240	Propionic acid	丙酸			A		A		DSXX-PXX-TPTP-XX
241	Ethyl propionate	丙酸乙酯	A	A		A	A		DSXX-AAX-UEXS-XX
242	Isopropyl Alcohol (Propanol) (Propyl alcohol)	丙醇	A	A	A	A	A	A	DSXX-AAX-UEXS-XX
243	Ethyl silicate	四乙氧基矽烷	B	A			A	B	DSXX-AAX-TAXS-XX
244	Tetraethyl lead	四乙鉛	B	A	A		A	C	DSXX-PXX-TPTP-XX
245	Tetrapropylene	四丙烯					A		
246	Tetrahydronaphthalene (Tetralin)	四氫化萘	A	A	C	A	A		DSXX-AAX-UEXS-XX
247	Tetrahydrofuran	四氫呋喃	D	A	C	A	A	B	DSXX-SAX-USXS-XX
248	Tetrahydrothiophene	四氫噻吩					A		
249	Tetrachloroethylene (Tetrachloroethene)	四氯乙烯			A	A	A		DSXX-PXX-TPTP-XX
250	Tetrachloroethane (Acetylene Tetrachloride)	四氯乙烷	D	C	D	A	A	D	
251	Titanium tetrachloride	四氯化鈦	D	B	B		A	D	DSXX-PXX-TPTP-XX
252	Stannic chloride (wet)	四氯化錫(濕)	D	D	A		A 20°C	A	DSXX-PXX-TPTP-XX
253	Stannic chloride (dry)	四氯化錫(乾)		A			A		DSXX-SAX-TSXS-XX
254	Tetrachloromethane (dry)	四氯甲烷(乾)	D	A	D	A	A	D	DSXX-SAX-USXS-XX
255	Tetrachloromethane (wet)	四氯甲烷(濕)		A		A	A		DSXX-SAX-USXS-XX
256	Butter	奶油	A	A	A		A		DSXX-SAX-TSXS-XX
257	pentanedioic acid	戊二酸					A		
258	Pentyl chloride	戊基氯					A		
259	Amyl chloronaphthalene	戊基氯萘					A	C	
260	Amyl naphthalene	戊基萘					A		

A = Excellent B = Good Minor, Effect, slight corrosion or discoloration. C = Fair Moderate/Effect, not recommended for continuous use. Softening, loss of strength, swelling may occur. D = Severe Effect, not recommended for ANY use.									
No.	English Name	Chinese Name	接液部材質 Material of Wetted Body			主隔膜材質 Material of Main Diaphragm			推薦規格 Recommended Specifications
			鋁 (AL)	不銹鋼 (SUS316)	聚丙烯 (PP)	超高分子聚乙烯 (UPE)	鐵氟龍 (Teflon)	熱塑性橡膠 (Santoprene)	
261	Pentene	戊烯				A			
262	Pentane	戊烷		B		A	A	A	DSXX-SAX-OSXS-XX
263	Pentane dion	戊烷二酮					A		
264	Amyl alcohol (Pentyl alcohol)	戊醇	A	A	A	A	A	B	DSXX-AAX-UEXS-XX
265	Butylamine	正丁胺	A	A		A		A	DSXX-AAX-UEXS-XX
266	n-Hexane	正己烷				A	A		
267	Nonyl alcohol(Nonanol)	正壬醇				A			
268	Chloropropane	正丙基氯					A		
269	Pentanol	正戊醇		A			A		DSXX-SAX-TSXS-XX
270	Decyl alcohol	正癸醇					A		
271	Corn oil	玉米油	A	A	A		A	B	DSXX-SAX-TSXS-XX
272	Glyceroltrioleate acid	甘油三油酸					A 60°C		
273	Glycol	甘醇	A		A	A	A 20°C	A	DSXX-AAX-UEXS-XX
274	Toluene (Toluol)	甲苯	A	A	D	A	A	C	DSXX-AAX-UEXS-XX
275	Toluene diisocyanate	甲苯二異氰酸酯					A	B	
276	Tolyamine	甲苯胺					A		
277	Methoxy propanol	甲氧基丙醇				A			
278	Methylamine, aqueous	甲胺·含水	A		A	A	A	A	DSXX-AAX-UEXS-XX
279	Methyl pentamethylene	甲基五亞甲基					A		
280	Methacrylic acid	甲基丙烯酸						A	
281	Methyl methacrylate	甲基丙烯酸甲酯	B	B		A	A	B	DSXX-AAX-UEXS-XX
282	Alphamethyl styrene	甲基苯乙烯				A			
283	Methylaniline (Methyl phenylamine)	甲基苯胺					A		
284	Methyl Amyl alcohol	甲基異丁基甲醇	A	A			A 20°C		DSXX-AAX-TAXS-XX
285	Diisobutyl ketone	甲基異丁基酮	A	A			A		DSXX-AAX-TAXS-XX
286	Methyl isopropyl ketone	甲基異丙基酮		A	C		A	C	DSXX-SAX-TSXS-XX
287	Methylcellosolve (ether)	甲基溶纖劑 (醚)					A		
288	Methyl cyclopentane	甲基環戊烷		A			A	C	DSXX-SAX-TSXS-XX
289	Methane	甲烷		A	A		A	C	DSXX-PXX-TPTP-XX

A = Excellent

B = Good Minor, Effect, slight corrosion or discoloration.

C = Fair Moderate/Effect, not recommended for continuous use. Softening, loss of strength, swelling may occur.

D = Severe Effect, not recommended for ANY use.

No.	English Name	Chinese Name	接液部材質 Material of Wetted Body			主隔膜材質 Material of Main Diaphragm			推薦規格 Recommended Specifications
			鋁 (AL)	不銹鋼 (SUS316)	聚丙稀 (PP)	超高分子聚乙烯 (UPE)	鐵氟龍 (Teflon)	熱塑性橡膠 (Santoprene)	
290	Methane amide	甲烷酰胺					A		
291	Methane carbonyl chloride	甲烷碳酰氯					A		
292	Methane carbonyl acetone	甲烷羰基丙酮					A		
293	Methane carbonyl nitrile	甲烷羰基腈					A		
294	Methane carbonyl amide	甲烷羰基酰胺					A		
295	Cresol	甲酚	A	A		B 60%	A		DSXX-AAX-TAXS-XX
296	Formicacid	甲酸					A	A	
297	Ethyl formiate	甲酸乙酯					A	A	
298	Methyl formate	甲酸甲酯	A	A			A	B	DSXX-AAX-TAXS-XX
299	Methyl alcohol	甲醇	B	A	A	A	A 20°C	A	DSXX-PXX-TPTP-XX
300	Formaldehyde (Formalin)	甲醛	A	A	A	A 40%	A 20°C	B	DSXX-AAX-UEXS-XX
301	Formamide	甲醯胺	A	B			A	A	DSXX-AAX-TAXS-XX
302	Alum	白礬		B	A	A	A	A	DSXX-PXX-OTPT-XX
303	Brandy	白蘭地酒		A			A		DSXX-SAX-TSSS-XX
304	Lime water	石灰水	D	B	A	A	A	A	DSXX-PXX-OTPT-XX
305	Petroleum	石油	B	A	A	A	A		DSXX-PXX-TPTP-XX
306	Petroleum ether	石油醚	B			A			
307	Carbolic acid	石炭酸	A	B	A		A	A	DSXX-AAX-OXXX-XX
308	Naphta	石腦油			A	A	A 20°C	C	DSXX-PXX-TPTP-XX
309	Paraffin	石蠟		A	A	A	A 60°C		DSXX-PXX-TPTP-XX
310	Perchloroethylene	全氯乙烯			A	A	A	D	DSXX-PXX-TPTP-XX
311	Paraformaldehyde	多聚甲醛	A		A		A		DSXX-AAX-TAXS-XX
312	Sodium hypochlorite (Bleach Liquid)-20%	次氯酸鈉 (漂白水) (20%)		A	A	A	A		DSXX-PXX-TPTP-XX
313	Sodium hypochlorite (Bleach Liquid)-wet	次氯酸鈉 (漂白水) (濕)		C	B	A	A	B	DSXX-PXX-TPTP-XX
314	Sodium hypochlorite (Bleaching Powder)-dry	次氯酸鈉 (漂白粉) (乾)		A			A		DSXX-SAX-TSXS-XX
315	Calcium hypochlorite (dry)	次氯酸鈣 (乾)	D	A	A		A	A	DSXX-PXX-OTPT-XX
316	Calcium hypochlorite (wet)	次氯酸鈣 (濕)	D	C	A	A	A	A	DSXX-PXX-OTPT-XX
317	Sewage	汙水	A	A	A	A	A	A	DSXX-AAX-UEXS-XX

A = Excellent B = Good Minor, Effect, slight corrosion or discoloration. C = Fair Moderate/Effect, not recommended for continuous use. Softening, loss of strength, swelling may occur. D = Severe Effect, not recommended for ANY use.									
No.	English Name	Chinese Name	接液部材質 Material of Wetted Body			主隔膜材質 Material of Main Diaphragm			推薦規格 Recommended Specifications
			鋁 (AL)	不銹鋼 (SUS316)	聚丙烯 (PP)	超高分子聚乙烯 (UPE)	鐵氟龍 (Teflon)	熱塑性橡膠 (Santoprene)	
318	Sewage sludge	汙泥	B	A	A	A	B	A	DSXX-AAX-OXXX-XX
319	Lanolin	羊毛脂		A	B		A		DSXX-PXX-TPTP-XX
320	Pyrrole	吡咯					A	C	
321	Pyrrolidine	吡咯烷		A					
322	Pyridine	吡啶		B	A	A	A 20°C	A	DSXX-PXX-OTPT-XX
323	Pyridine oil	吡啶油					A		
324	Furane	呋喃					A	C	
325	Tall oil	妥尔油脂肪酸 (松油)		A		A	A		DSXX-SAX-TSXS-XX
326	Urine	尿		A	A		A	A	DSXX-PXX-OTPT-XX
327	Mercury	汞					A 20°C	A	
328	Mercury salt	汞鹽		A		A	A		DSXX-SAX-USXS-XX
329	Gasoline / Petrol	汽油 / 汽油	A	A	B	B	B 60°C	C	DSXX-AAX-TAXS-XX
330	Benzylamine	苄胺		B					
331	Octene	辛烯					A		
332	Capryl Alcohol (Octanol) (Octyl alcohol)	辛醇	A	A	A	A	A		DSXX-AAX-UEXS-XX
333	Skydrol	防火航空液壓油		A	B		A	B	DSXX-SAX-TSXS-XX
334	Latex - conserved with ammonia	乳汁 - 與氨保存	A	A			A		DSXX-SAX-TSXS-XX
335	Lacticacid - aqueous	乳酸 - 含水	C	B	A		A	A	DSXX-PXX-OTPT-XX
336	Lactol	乳醇	A	A			A		DSXX-AAX-TAXS-XX
337	Methylene pentane-35°C	亞甲基戊烷 - 35°C					A		
338	Linoleic acid	亞油酸	A	A	A		A	B	DSXX-SAX-TAXS-XX
339	Sulfurousacid 10%	亞硫酸 10%	C	C	A	A	A		DSXX-PXX-TPTP-XX
340	Sulfurousacid 75%	亞硫酸 75%	C	C	B	A	A		DSXX-PXX-TPTP-XX
341	Sodium bisulfite	亞硫酸氫鈉		B	A	A	A	A	DSXX-PXX-OTPT-XX
342	Calcium bisulfite	亞硫酸氫鈣	D	A			A		DSXX-SAX-TSXS-XX
343	Potassium bisulfite	亞硫酸氫鉀	B	B			A		DSXX-AAX-TAXS-XX
344	Bisulfite lye	亞硫酸氫鹽灰汁				A			
345	Sodium sulfite	亞硫酸鈉		B		A	A 20°C		DSXX-SAX-USXS-XX
346	Calcium sulfite	亞硫酸鈣	B	A			A		DSXX-SAX-TSXS-XX

A = Excellent

B = Good Minor, Effect, slight corrosion or discoloration.

C = Fair Moderate/Effect, not recommended for continuous use. Softening, loss of strength, swelling may occur.

D = Severe Effect, not recommended for ANY use.

No.	English Name	Chinese Name	接液部材質 Material of Wetted Body			主隔膜材質 Material of Main Diaphragm			推薦規格 Recommended Specifications
			鋁 (AL)	不銹鋼 (SUS316)	聚丙烯 (PP)	超高分子聚乙烯 (UPE)	鐵氟龍 (Teflon)	熱塑性橡膠 (Santoprene)	
347	Potassium sulfite	亞硫酸鉀	A	B	A		A		DSXX-AAX-TAXS-XX
348	Linseed oil	亞麻仁油	A	A	A		A	B	DSXX-AAX-TAXS-XX
349	Linolenic acid	亞麻酸					A		
350	Sodium chlorite	亞氯酸鈉		B		A	A	B	DSXX-SAX-USXS-XX
351	Sodium nitrite	亞硝酸鈉		B	A		A		DSXX-PXX-TPTP-XX
352	Potassium nitrite	亞硝酸鉀	B	A			A		DSXX-SAX-TSXS-XX
353	Potassium ferrocyanide	亞鐵氰化鉀	B	B	A		A 100°C	A	DSXX-PXX-TPTP-XX
354	Butyl phenol	叔丁基苯酚		B					
355	Butyl chloride	叔丁基氯	D	B	D		A		DSXX-SAX-TSXS-XX
356	Coffee	咖啡		A	A	A	A	A	DSXX-PXX-OPTP-XX
357	Heptane	庚烷		A	A	A	A	C	DSXX-PXX-TPTP-XX
358	Allofumaric acid	延胡索酸					A		
359	Mercuric chloride (dry)	昇汞 (乾)		A				A	DSXX-SAX-OSXS-XX
360	Mercuric chloride (wet)	昇汞 (濕)		C				A	
361	Gelatine	明膠	A	A	A	A	A 20°C	A	DSXX-AAX-UEXS-XX
362	Potassium aluminum sulfate	明礬			A	A			DSXX-PXX-TPTP-XX
363	Pine oil	松油		A			A	C	DSXX-SAX-TSXS-XX
364	Rosin oil	松香油		A			A		DSXX-SAX-TSXS-XX
365	Turpentine	松節油		A		A	A	C	DSXX-SAX-USXS-XX
366	Fruitjuices	果汁	B	A	A	A	A 20°C	A	DSXX-SAX-TSXS-XX
367	Oil	油	A	A		A	A 20°C		DSXX-AAX-UEXS-XX
368	Hydr. oil phosphate ester based	油性磷酸酯基			B		A		DSXX-PXX-TPTP-XX
369	Fat, animal	油脂・動物	A	A	B		A		DSXX-PXX-TPTP-XX
370	Fat, vegetable	油脂・菜	A	A	B		A		DSXX-PXX-TPTP-XX
371	Paint	油漆	A	A		A	A		DSXX-AAX-UEXS-XX
372	Grease, lubricant	油膏・潤滑劑	A	A	A	A	A	D	DSXX-PXX-TPTP-XX
373	Butyl oleate	油酸丁酯					A	C	
374	n-Butyl oleate	油酸正丁酯				A			
375	Methyl oleate	油酸甲酯					A	C	
376	Alkynes	炔					A		

A = Excellent B = Good Minor, Effect, slight corrosion or discoloration. C = Fair Moderate/Effect, not recommended for continuous use. Softening, loss of strength, swelling may occur. D = Severe Effect, not recommended for ANY use.									
No.	English Name	Chinese Name	接液部材質 Material of Wetted Body			主隔膜材質 Material of Main Diaphragm			推薦規格 Recommended Specifications
			鋁 (AL)	不銹鋼 (SUS316)	聚丙烯 (PP)	超高分子聚乙烯 (UPE)	鐵氟龍 (Teflon)	熱塑性橡膠 (Santoprene)	
377	Silicone oil	矽油(硅油)	A	A	A	A	A	A	DSXX-AAX-UEXS-XX
378	Sodium metasilicate	矽酸鈉		A				A	DSXX-SAX-OSXS-XX
379	Calcium silicate	矽酸鈣	A	A			A		DSXX-AAX-TAXS-XX
380	Potassium silicate (solution in water)	矽酸鉀 (水中溶液)	B	B			A		DSXX-AAX-TAXS-XX
381	Magnesium silicate	矽酸鎂			A		A		DSXX-PXX-TPTP-XX
382	Soap solutions	肥皂溶液	A	A	A		A	A	DSXX-AAX-OXXX-XX
383	Mustard	芥末		A	A		A	A	DSXX-SAX-TSXS-XX
384	Peanut oil	花生油	A	A	A		A	B	DSXX-SAX-TSXS-XX
385	Aromatic solvent	芳烴溶劑	A	A			B 60°C		
386	Benzyl alcohol 100%	苄醇 (100%)	A	A	B	A	A 100°C	A	DSXX-AAX-UAXX-XX
387	Piperidine	哌啶					A	B	
388	Quinine	奎寧	D	B					
389	Whiskey and wines	威士忌和酒	A	A	C		A	A	DSXX-SAX-TSXS-XX
390	Citrus oil	柑橘油		A			A		DSXX-SAX-TSXS-XX
391	Salicylic acid	柳酸	A		A	A	A 20°C		DSXX-AAX-UEXS-XX
392	Sodium fluoride	氟化鈉	B	C	A		A	A	DSXX-PXX-TPTP-XX
393	Calcium fluoride	氟化鈣		C					
394	Potassium fluoride	氟化鉀		C					
395	Freon	氟利昂		A	A		A	D	DSXX-PXX-TPTP-XX
396	Fluosilicic Acid (Sand Acid)	氟矽酸	D		A	A	A	A	DSXX-PXX-TPTP-XX
397	Fluorobenzene	氟苯	D		D		A	C	
398	Fluorine (dry)	氟素(乾)		A		A	A 20°C	D	DSXX-SAX-TSXS-XX
399	Fluorine (wet)	氟素(濕)		C			B	D	
400	Fluoroboricacid 65%	氟硼酸 65%			A		A		DSXX-PXX-TPTP-XX
401	Detergent 2%	洗滌劑 2%	C	A	A			B	DSXX-PXX-TPTP-XX
402	Isotridecanol	界面活性劑			A	A	A		DSXX-PXX-TPTP-XX
403	Diethyl sebacate	癸二酸二乙酯			A		A	B	DSXX-PXX-TPTP-XX
404	Dibutyl sebacate	癸二酸二丁酯			A	A	A	B	DSXX-PXX-TPTP-XX
405	Dioctyl sebacate	癸二酸二辛酯	A			A		C	DSXX-AAX-UAXX-XX
406	Dibenzyl sebacate	癸二酸二苄酯					A	C	

A = Excellent B = Good Minor, Effect, slight corrosion or discoloration. C = Fair Moderate/Effect, not recommended for continuous use. Softening, loss of strength, swelling may occur. D = Severe Effect, not recommended for ANY use.									
No.	English Name	Chinese Name	接液部材質 Material of Wetted Body			主隔膜材質 Material of Main Diaphragm			推薦規格 Recommended Specifications
			鋁 (AL)	不銹鋼 (SUS316)	聚丙烯 (PP)	超高分子聚乙烯 (UPE)	鐵氟龍 (Teflon)	熱塑性橡膠 (Santoprene)	
407	Decane	癸烷			A		A	C	DSXX-PXX-TPTP-XX
408	Wine	紅酒(水果酒)	B	A	A	B	A	A	DSXX-SAX-TSXS-XX
409	Bordeaux	紅葡萄酒	B	A	A	A	A	B	DSXX-PXX-TPTP-XX
410	Caustic soda	苛性鈉	C	B	A		A 60°C		DSXX-PXX-TPTP-XX
411	Caustic potash	苛性鉀	D	A	A		A	A	DSXX-PXX-OTPT-XX
412	Picric acid	苦味酸	A	B	A	A	20°C	B	DSXX-AAX-UEXS-XX
413	Benzene (Benzol)	苯	A	A	D	A	A	C	DSXX-AAX-UEXS-XX
414	Benzene benzol, mixed	苯 (混合的)	A	A	D	A	A	C	DSXX-AAX-UEXS-XX
415	Styrene (Vinylbenzene)	苯乙烯	A	A		A	A	C	DSXX-AAX-UEXS-XX
416	Phenylethyl alcohol	苯乙醇					A		
417	Phenylmethyl ketone	苯甲基酮					A		
418	Benzoic acid, aqueous	苯甲酸, 含水			A	A	A 60°C		DSXX-PXX-TPTP-XX
419	Ethyl benzoate	苯甲酸乙酯	A	A	B		A	C	DSXX-AAX-TAXS-XX
420	Butyl benzoate	苯甲酸丁酯			A	A			DSXX-PXX-TPTP-XX
421	Methyl benzoate	苯甲酸甲酯				A			
422	Benzyl benzoate	苯甲酸苄酯	A	B			A	D	DSXX-AAX-TAXS-XX
423	Benzene benzol ethanol (Phenylmethanol)-mixed	苯甲醇 (混合的)	A	A	D	A	A	C	DSXX-AAX-UEXS-XX
424	Benzaldehyde	苯甲醛	A		A	A	60°C	B	DSXX-AAX-UEXS-XX
425	Benzoyl chloride	苯甲酰氯	D	B			A		DSXX-SAX-TSXS-XX
426	Phenyl hydrazine	苯肼	A		D	A	A	B	DSXX-AAX-UEXS-XX
427	Aniline	苯胺	A	B	A	A	A 60°C	B	DSXX-PXX-TPTP-XX
428	Aniline dyes	苯胺染料		B	A		A	B	DSXX-PXX-TPTP-XX
429	Aniline hydrochloride	苯胺鹽酸鹽	D	D	D	A	A	A	
430	Benzenesulfonic acid 15%	苯磺酸 (15%)	C	A			A	A	DSXX-SAX-TSTS-XX
431	Water, heavy (deuterium)	重水				A	A 20°C		DSXX-SAX-USXS-XX
432	Noble metal chloride solvent	重金屬氯化物溶劑				A			
433	Potassium dichromate	重鉻酸鉀		A	A	A	A 20°C	A	DSXX-PXX-OTPT-XX
434	Airplane fuel	飛機燃料		A			A		DSXX-SAX-TSTS-XX
435	Petroleum(Crude Oil) (Sour)	原油	B	A	D	A	A		DSXX-AAX-UEXS-XX

A = Excellent

B = Good Minor, Effect, slight corrosion or discoloration.

C = Fair Moderate/Effect, not recommended for continuous use. Softening, loss of strength, swelling may occur.

D = Severe Effect, not recommended for ANY use.

No.	English Name	Chinese Name	接液部材質 Material of Wetted Body			主隔膜材質 Material of Main Diaphragm			推薦規格 Recommended Specifications
			鋁 (AL)	不銹鋼 (SUS316)	聚丙烯 (PP)	超高分子聚乙烯 (UPE)	鐵氟龍 (Teflon)	熱塑性橡膠 (Santoprene)	
436	Diesel oil	柴油	A	A	B	A	A 20°C	C	DSXX-AAX-UEXS-XX
437	Walnut oil	核桃油		A			A		DSXX-SAX-TSXS-XX
438	Chinese wood oil	桐油		A			A		DSXX-SAX-TSXS-XX
439	Nitrogen oxide	氧化氮					A	D	
440	Sodium monoxide	氧化鈉	C		A	A	A		DSXX-PXX-TPTP-XX
441	Calcium oxide	氧化鈣		A			A 20°C		DSXX-SAX-TSXS-XX
442	Aluminium oxide	氧化鋁		A		A			DSXX-SAX-USXS-XX
443	Zinc oxide	氧化鋅					A		
444	Magnesium oxide (Magnesia Alba)	氧化鎂	A	A			A	A	DSXX-AAX-TAXS-XX
445	Oxygen	氧氣	A	A	70°C		A		DSXX-AAX-TAXS-XX
446	Ammonia water	氨水		A	A	A	A		DSXX-PXX-TPTP-XX
447	Ethanolamine	氨基乙醇	B	A	D	A	A	A	DSXX-SAX-USXS-XX
448	Lead sulfamate	氨基磺酸鉛	C	C	A		A	A	DSXX-PXX-TPTP-XX
449	Sea Water	海水	C	A	A	A	A	A	DSXX-PXX-OTPT-XX
450	Arsenic acid, all concentrations	砷酸 (全濃縮)			A		A		DSXX-PXX-TPTP-XX
451	Lead arsenate	砷酸鉛				A			
452	Copper arsenate, basic	砷酸銅					A		
453	Laughing gas	笑氣			A		A		DSXX-PXX-TPTP-XX
454	Animal fat	脂肪		A	A	A	A	C	DSXX-PXX-TPTP-XX
455	Fatty acids	脂肪酸	A	A	B	A	A	B	DSXX-AAX-UEXS-XX
456	Ozone	臭氧	A		C	A	A 20°C	A	DSXX-AAX-UEXS-XX
457	Anisole	茴香醚	B	B			A		DSXX-AAX-TAXS-XX
458	Tartaric acid	酒石酸	B	A	A	A	A	A	DSXX-PXX-TPTP-XX
459	Alcohol	酒精	A	A	A		A		DSXX-SAX-TSXS-XX
460	Cis-butenedioic acid	馬來酸					A		
461	Tall fatty acid	高脂肪酸				A			
462	Tar oil	高粘重質原油		A		A			DSXX-SAX-USXS-XX
463	Perchloric acid	高氯酸			A		A 20°C	C	DSXX-PXX-TPTP-XX
464	Blast furnace gas	高爐煤氣					A	A	

A = Excellent

B = Good Minor, Effect, slight corrosion or discoloration.

C = Fair Moderate/Effect, not recommended for continuous use. Softening, loss of strength, swelling may occur.

D = Severe Effect, not recommended for ANY use.

No.	English Name	Chinese Name	接液部材質 Material of Wetted Body			主隔膜材質 Material of Main Diaphragm			推薦規格 Recommended Specifications
			鋁 (AL)	不銹鋼 (SUS316)	聚丙烯 (PP)	超高分子聚乙烯 (UPE)	鐵氟龍 (Teflon)	熱塑性橡膠 (Santoprene)	
465	Sodium metaphosphate	偏磷酸鈉	A		A	A	A	A	DSXX-AAX-UEXS-XX
466	Azobenzene	偶氮苯					A		
467	Oils, animal	動物油	A	A	A	A	A 20°C		DSXX-PXX-TPTP-XX
468	Beer	啤酒	B	A	A		A 60°C		DSXX-PXX-TPTP-XX
469	Hydr. oil glycol based	基于油乙二醇	A		A		A		DSXX-AAX-TAXS-XX
470	Feces	排泄物	B	A	A	A	A	B	DSXX-PXX-TPTP-XX
471	Hydrogen sulfide, dry - cold	氫化硫 · 乾燥 - 冷		A		A	A	A	DSXX-SAX-TSXS-XX
472	Hydrogen sulfide, wet - cold	氫化硫 · 濕 - 冷		A			A		DSXX-SAX-TSXS-XX
473	Hydrofluoric acid	氫氟酸	D	D			A	D	
474	Fluorhydrogen acid 10%	氫氟酸 10%	D	C	A	A	A	D	DSXX-PXX-TPTP-XX
475	Sodium hydroxide	氫氧化鈉	C	B	A	A 20°C	A 100°C	A	DSXX-PXX-OTPT-XX
476	Calcium hydroxide (Slaked lime)	氫氧化鈣(熟石灰)		B	A	A	A	A	DSXX-PXX-TPTP-XX
477	Potash lye	氫氧化鉀			A	A	A		DSXX-PXX-TPTP-XX
478	Chromic hydroxide	氫氧化鉻		B					
479	Ammonium hydroxide (max. to 50%)	氫氧化銨 (最大至 50%)	A	A	A	A	A	A	DSXX-PXX-OTPT-XX
480	Ammonium hydroxide (wet)	氫氧化銨 (濕)		A	A	A	A 60°C		DSXX-PXX-TPTP-XX
481	Aluminium hydroxide	氫氧化鋁		A	A		A	A	DSXX-PXX-OTPT-XX
482	Barium hydroxide 65°C	氫氧化鋇 (65°C)		A	A		A	A	DSXX-PXX-OTPT-XX
483	Lithium hydroxide	氫氧化鋰	D	B			A		DSXX-SAX-TSXS-XX
484	Magnesium hydroxyde	氫氧化鎂	C	A			A	A	DSXX-SAX-TSXS-XX
485	Hydrocyanic Acid (Prussic acid) - 20%	氫氰酸 - 20%		C	A	A	A	B	DSXX-PXX-TPTP-XX
486	Hydrobromic acid	氫溴酸	D	D	B		A 20°C	B	DSXX-PXX-TPTP-XX
487	Hydroborofluoric acid	氫硼氟酸					A		
488	Paraffin oil	液態石蠟	A	A	A	A	A	A	DSXX-AAX-UAXX-XX
489	Liquid manure	液態肥料			A		A		DSXX-PXX-TPTP-XX
490	Liquid ammonia	液態氨				A	A	A	
491	Allyl chloride	烯丙基氯			A		A		DSXX-PXX-TPTP-XX
492	Allyl bromide	烯丙基溴	D			A	A		
493	Allyl alcohol	烯丙醇	B	A		A	A		DSXX-SAX-TSTS-XX

A = Excellent B = Good Minor, Effect, slight corrosion or discoloration. C = Fair Moderate/Effect, not recommended for continuous use. Softening, loss of strength, swelling may occur. D = Severe Effect, not recommended for ANY use.									
No.	English Name	Chinese Name	接液部材質 Material of Wetted Body			主隔膜材質 Material of Main Diaphragm			推薦規格 Recommended Specifications
			鋁 (AL)	不銹鋼 (SUS316)	聚丙烯 (PP)	超高分子聚乙烯 (UPE)	鐵氟龍 (Teflon)	熱塑性橡膠 (Santoprene)	
494	Olefins	烯烴					A		
495	Alkanes	烷		A			A		DSXX-SAX-TSTS-XX
496	Alkylbenzol	烷基苯				A			
497	Sugar beet juices	甜菜汁		A	A	A	A	A	DSXX-SAX-TSXS-XX
498	Beet sugar syrup	甜菜糖糖漿		A				A	DSXX-SAX-OSXS-XX
499	Isobutylamine	異丁胺				A			
500	Diisobutylene	異丁烯	B		A	A	A	C	DSXX-PXX-TPTP-XX
501	Isobutane	異丁烷					A		
502	Isobutyl alcohol (Isobutanol)	異丁醇	A		A	A 70°C	A		DSXX-AAX-UEXS-XX
503	Isododecane	異十二烷	B	B			A		DSXX-AAX-TAXS-XX
504	Isooctadecyl alcohol	異十八烷醇				A			
505	Isotridecyl alcohol	異十三烷醇				A			
506	Isohexadecyl alcohol	異十六烷醇				A			
507	Isononyl alcohol	異壬醇				A			
508	Mesityl oxyde	異丙叉丙酮	A				A	C	DSXX-AAX-TAXS-XX
509	Cumeme (Isopropylbenzene)	異丙苯	B	B			A		DSXX-AAX-TAXS-XX
510	Isopropyl amine	異丙胺		A			A		DSXX-SAX-TSXS-XX
511	Isopropyl chloride	異丙基氯	D	A	D		A	C	DSXX-SAX-TSXS-XX
512	Isopropenyl benzol	異丙烯苯				A			
513	Isopropyl ether (Diisopropyl ether)	異丙醚	A		B	A	A	C	DSXX-AAX-UEXS-XX
514	Isopentane	異戊烷					A		
515	Isoamyl alcohol	異戊醇					A		
516	Isophorone	異佛爾酮	A	A		A	A	B	DSXX-AAX-UAXX-XX
517	Isooctanol	異辛醇				A			
518	Isodecyl alcohol	異癸醇				A			
519	Silicic acid	硅酸					A		
520	Sodium silicate	硅酸鈉	A	A			A		DSXX-AAX-TAXS-XX
521	Silicone liquids	硅樹脂液體					A 20°C		
522	Sodium sulfide	硫化鈉	D	B	A		A	A	DSXX-PXX-TPTP-XX
523	Calcium sulfide	硫化鈣			A		A	A	DSXX-PXX-OTPT-XX

A = Excellent

B = Good Minor, Effect, slight corrosion or discoloration.

C = Fair Moderate/Effect, not recommended for continuous use. Softening, loss of strength, swelling may occur.

D = Severe Effect, not recommended for ANY use.

No.	English Name	Chinese Name	接液部材質 Material of Wetted Body			主隔膜材質 Material of Main Diaphragm			推薦規格 Recommended Specifications
			鋁 (AL)	不銹鋼 (SUS316)	聚丙烯 (PP)	超高分子聚乙烯 (UPE)	鐵氟龍 (Teflon)	熱塑性橡膠 (Santoprene)	
524	Potassium sulfide	硫化鉀	D	B	A		A 100°C		DSXX-PXX-TPTP-XX
525	Ammonium sulfide	硫化銨	B	B		A	A		DSXX-AAX-UEXS-XX
526	Aluminium sulfide	硫化鋁	C	A	A	A			DSXX-PXX-TPTP-XX
527	Barium sulfide	硫化鋇		B	A		A	A	DSXX-PXX-OPTP-XX
528	Sodium thiosulfate	硫代硫酸鈉	A	B	A	A	A		DSXX-AAX-UEXS-XX
529	Potassium thiosulfate	硫代硫酸鉀					A		
530	Ammonium thiosulfate	硫代硫酸銨	A	A			A	A	DSXX-AAX-TAXS-XX
531	Sodium hydrogen sulfide	硫化氫鈉				A			
532	Ammonium thiocyanate	硫氰酸銨	C	A			A		DSXX-SAX-TSXS-XX
533	Sulfuric acid (Under 75%)	硫酸 (75%以內)	C	C	A	A 50°C	A	A	DSXX-PXX-TPTP-XX
534	Sulfuric acid 100%	硫酸 100%	C	A	C	A	A		DSXX-SAX-TSXS-XX
535	Sulfuric acid 80%-95%	硫酸 80%-95%	C	B	B		A		DSXX-SAX-TSXS-XX
536	Sulfuric acid 90%	硫酸 90%	C	B	B		A		DSXX-SAX-TSXS-XX
537	Sulfuric acid 95%-100%	硫酸 95%-100%	C	A	C		A		DSXX-SAX-TSXS-XX
538	Ethyl sulfate	硫酸乙酯	A	D			A	B	DSXX-AAX-TAXS-XX
539	Dimethyl sulfate	硫酸二甲酯		B					DSXX-SAX-TSXS-XX
540	Ferrous sulfate	硫酸亞鐵	A	B	A	A	A 20°C	A	DSXX-AAX-UEXS-XX
541	Sulfuric acid anhydride	硫酸酐					A		
542	Sodium bisulfate	硫酸氫鈉	C	A	A		A		DSXX-PXX-TPTP-XX
543	Potassium bisulfate	硫酸氫鉀	A 10%	A 10%	A	A	A		DSXX-PXX-TPTP-XX
544	Sodium sulfate	硫酸鈉	B	A		A	A	A	DSXX-SAX-OSXS-XX
545	Calcium sulfate	硫酸鈣	C	B	A	A	A		DSXX-PXX-TPTP-XX
546	Potassium sulfate	硫酸鉀		B	A	A	A 100°C	A	DSXX-PXX-OPTP-XX
547	Potassium chromium sulfate	硫酸鉀鉻				A			
548	Lead sulfate	硫酸鉛	D		A				
549	Chromium sulfate	硫酸鉻	B	B					
550	Copper sulfate - 65°C	硫酸銅 - 65°C	C	B	A		A	A	DSXX-PXX-OPTP-XX
551	Ammonium sulfate	硫酸銨	C	B	A	A		A	DSXX-PXX-OPTP-XX
552	Aluminium sulfate (aqueous) 65°C	硫酸鋁 (含水) 65°C	C	A	A	A	A 60°C		DSXX-PXX-TPTP-XX
553	Aluminium salt solution	硫酸鋁溶液		A	A			A	DSXX-PXX-OPTP-XX

A = Excellent

B = Good Minor, Effect, slight corrosion or discoloration.

C = Fair Moderate/Effect, not recommended for continuous use. Softening, loss of strength, swelling may occur.

D = Severe Effect, not recommended for ANY use.

No.	English Name	Chinese Name	接液部材質 Material of Wetted Body			主隔膜材質 Material of Main Diaphragm			推薦規格 Recommended Specifications
			鋁 (AL)	不銹鋼 (SUS316)	聚丙烯 (PP)	超高分子聚乙烯 (UPE)	鐵氟龍 (Teflon)	熱塑性橡膠 (Santoprene)	
554	Zinc sulfate	硫酸鋅	C	A	A	A	A 80°C	A	DSXX-PXX-TPTP-XX
555	Barium sulfate	硫酸鋇		B	A			A	DSXX-PXX-OTPT-XX
556	Magnesium sulfate	硫酸鎂	A	A	A	A	A 100°C	A	DSXX-AAX-UEXS-XX
557	Magnesium ammonium sulfate	硫酸鎂銨					A		
558	Cadmium sulfate	硫酸鎘		A					
559	Nickel sulfate (aqueous)	硫酸鎳 (含水)	A		A	A	A	A	DSXX-AAX-UEXS-XX
560	Ferric sulfate	硫酸鐵		A			A	A	DSXX-SAX-OSXS-XX
561	Sulfate liquor, black	硫酸鹽酒·黑	C	A			A	A	DSXX-SAX-TSXS-XX
562	Mercaptane (Thio alcohol)	硫醇		A			A		DSXX-SAX-TSXS-XX
563	Sulfur, molten 90°C	硫磺·溶解90°C	B	A	C		A		DSXX-SAX-TSXS-XX
564	Sulfur anhydride	硫磺酐					A 60°C		
565	Sulfur ether	硫醚					A		
566	Phenol	酚	A	B	A	A	A 20°C	A	DSXX-AAX-UEXS-XX
567	Phenyl methanal	酚醛樹脂					A		
568	Phenolates	酚鹽					A		
569	Cool-liver oil	魚肝油		A	A		A		DSXX-PXX-TPTP-XX
570	Rotenone	魚藤酮					A		
571	Ammonium chloride (wet)	鹵砂 (濕)		C	A	A	A		DSXX-PXX-TPTP-XX
572	Ligroine	揮發油		A			A		DSXX-SAX-TSXS-XX
573	Cotton seed oil	棉籽油		A			A	A	DSXX-SAX-OSXS-XX
574	Palm oil	棕櫚油		A			A	B	DSXX-SAX-TSXS-XX
575	Palmiticacid	棕櫚酸	A		A	A	A	B	DSXX-AAX-UEXS-XX
576	Nitrogen	氮氣	A	A	A	A			DSXX-AAX-UEXS-XX
577	Chlorine (dry)	氯 (乾)	C	A			A 20°C	C	DSXX-SAX-TSXS-XX
578	Chlorine (bleach) (wet)	氯 (漂白)(濕)	C	C	A		A 20°C	C	DSXX-PXX-TPTP-XX
579	Vinyl chloride	氯乙烯	D	A	D	B	A	D	DSXX-SAX-TSXS-XX
580	Monochloroethane (Chloroethane)-dry	氯乙烷 (乾)	D	A		A	A		DSXX-SAX-TSXS-XX
581	Monochloroethane (Chloroethane)-wet	氯乙烷 (濕)	D	C		A	A		
582	Ethyl chloroacetate	氯乙酸乙酯				A			
583	Methyl chloroacetate	氯乙酸甲酯				A			

A = Excellent

B = Good Minor, Effect, slight corrosion or discoloration.

C = Fair Moderate/Effect, not recommended for continuous use. Softening, loss of strength, swelling may occur.

D = Severe Effect, not recommended for ANY use.

No.	English Name	Chinese Name	接液部材質 Material of Wetted Body			主隔膜材質 Material of Main Diaphragm			推薦規格 Recommended Specifications
			鋁 (AL)	不銹鋼 (SUS316)	聚丙烯 (PP)	超高分子聚乙烯 (UPE)	鐵氟龍 (Teflon)	熱塑性橡膠 (Santoprene)	
584	Chloroethanol	氯乙醇	B	A			A		DSXX-SAX-TSTS-XX
585	Chlorobutadiene	氯丁二烯	D	B	D		A	C	DSXX-SAX-TSTS-XX
586	Butyl chloride (Chlorobutane)	氯丁烷	D	B	D	A	A		DSXX-SAX-USXS-XX
587	Dichlorobutene	氯化丁烯					A		
588	Chlorine water 3%	氯化水 (3%)	C	B	A	A	A		DSXX-PXX-TPTP-XX
589	Mercury dichloride	氯化汞					A		
590	Thionyl chloride	氯化亞砷	D	A	B		A	B	DSXX-SAX-TSXS-XX
591	Stannous chloride (dry)	氯化亞錫 (乾)		A	A		A		DSXX-SAX-TSXS-XX
592	Stannous chloride (wet)	氯化亞錫 (濕)		C	A		A		DSXX-PPX-TPTP-XX
593	Ferrous chloride (dry)	氯化亞鐵 (乾)		A			A	A	DSXX-SAX-OSXS-XX
594	Ferrous chloride (wet)	氯化亞鐵 (濕)		C			A 25°C		
595	Benzyl chloride (dry)	氯化苄 (乾)		A			A		DSXX-SAX-TSTS-XX
596	Benzyl chloride (wet)	氯化苄 (濕)		C	B	A	A		
597	Sulfur chloride (dry)	氯化硫 (乾)		A			A		DSXX-SAX-TSXS-XX
598	Sulfur chloride (wet)	氯化硫 (濕)		C			A		
599	Sodium chloride (wet)	氯化鈉 (濕)	C	C	A	A	A 100°C	A	DSXX-PXX-OTPT-XX
600	Calcium chloride (dry)	氯化鈣 (乾)		A					
601	Calcium chloride (wet)	氯化鈣 (濕)		C	A	A	A 60°C	A	DSXX-PXX-OTPT-XX
602	Cobalt chloride	氯化鈷	D				A	A	
603	Potassium chloride (dry)	氯化鉀 (乾)		A					
604	Potassium chloride (wet)	氯化鉀 (濕)		C				A	
605	Cupric chloride	氯化銅	D					A	
606	Copper chloride (dry)	氯化銅 (乾)		A			A	A	DSXX-SAX-TSXS-XX
607	Copper chloride (wet)	氯化銅 (濕)	D	C	A		A		DSXX-PXX-TPTP-XX
608	Aluminium chloride - dry	氯化鋁 (乾)					A		
609	Aluminium chloride - wet	氯化鋁 (濕)	C	A		A	B 60°C	A	DSXX-SAX-OSXS-XX
610	Zinc chloride (dry)	氯化鋅 (乾)		A				A	DSXX-SAX-OSXS-XX
611	Zinc chloride (wet)	氯化鋅 (濕)		C	A		A		DSXX-PXX-TPTP-XX
612	Lithium chloride (dry)	氯化鋰 (乾)		A			A	A	
613	Lithium chloride (wet)	氯化鋰 (濕)	D	C	A				

A = Excellent

B = Good Minor, Effect, slight corrosion or discoloration.

C = Fair Moderate/Effect, not recommended for continuous use. Softening, loss of strength, swelling may occur.

D = Severe Effect, not recommended for ANY use.

No.	English Name	Chinese Name	接液部材質 Material of Wetted Body			主隔膜材質 Material of Main Diaphragm			推薦規格 Recommended Specifications
			鋁 (AL)	不銹鋼 (SUS316)	聚丙烯 (PP)	超高分子聚乙烯 (UPE)	鐵氟龍 (Teflon)	熱塑性橡膠 (Santoprene)	
614	Tin chloride/ Tin tetrachloride	氯化錫/ 四氯化錫	D	A	A	A	A	A	DSXX-PXX-OPTP-XX
615	Magnesium chloride(dry)	氯化鎂 (乾)		A					
616	Magnesium chloride(wet)	氯化鎂 (濕)	C	C	A	A	A	A	DSXX-PXX-TPTP-XX
617	Cadmium chloride (dry)	氯化鎘 (乾)		A					
618	Cadmium chloride (wet)	氯化鎘 (濕)		C					
619	Nickel chloride (dry)	氯化鎳 (乾)		A				A	
620	Nickel chloride (wet)	氯化鎳 (濕)	C	C			A	A	
621	Ferric chloride (Iron chloride)-dry	氯化鐵 (乾)		A					
622	Ferric chloride (Iron chloride)-wet	氯化鐵 (濕)	C	C	A	A	A	B	DSXX-PXX-TPTP-XX
623	Chloracetone	氯丙酮					A		
624	Chloromethane	氯代甲烷	C		A	A			DSXX-PXX-TPTP-XX
625	Amyl chloride (dry)	氯戊烷 (乾)		A					
626	Amyl chloride (wet)	氯戊烷 (濕)		C	B	A	A	C	DSXX-PXX-TPTP-XX
627	Chlorotoluene	氯甲苯	D	B	D		A	C	DSXX-SAX-TSXS-XX
628	Methyl chloride	氯甲烷	C		A		A		DSXX-PXX-TPTP-XX
629	Methyl chloride (dry)	氯甲烷 (乾)		A		A	A		DSXX-SAX-TSXS-XX
630	Methyl chloride (wet)	氯甲烷 (濕)		C			A		
631	Trichloromethane (dry)	氯仿 (乾)		A	C		A		DSXX-SAX-TSXS-XX
632	Trichloromethane (wet)	氯仿 (濕)		C	C		A		
633	Chlorobenzene (Monochlorobenzene)	氯苯	D	B	D		A	C	DSXX-SAX-TSXS-XX
634	Chlorine gas dry	氯氣體 (乾)	C		C	C	A	C	
635	Chlorine gas wet	氯氣體 (濕)	C		C	C	A	C	
636	Chlorophenol (Chlorophene)	氯酚	C	B			A		DSXX-SAX-TSXS-XX
637	Chloronaphthalene	氯萘	D				A	D	
638	Chlorobromomethane	氯溴甲烷	D	B	D		A	D	DSXX-SAX-TSXS-XX
639	Chloric acid (aqueous)	氯酸 (含水)		C	A		A		DSXX-PXX-TPTP-XX
640	Sodium chlorate (dry)	氯酸鈉(乾)		A					
641	Sodium chlorate (wet)	氯酸鈉(濕)		C	A	A	A	A	DSXX-PXX-OPTP-XX
642	Calcium chlorate	氯酸鈣	B	B	A		A		DSXX-PXX-TPTP-XX
643	Potassium chlorate	氯酸鉀	D	A	A		A	A	DSXX-PPX-TPTP-XX

A = Excellent B = Good Minor, Effect, slight corrosion or discoloration. C = Fair Moderate/Effect, not recommended for continuous use. Softening, loss of strength, swelling may occur. D = Severe Effect, not recommended for ANY use.									
No.	English Name	Chinese Name	接液部材質 Material of Wetted Body			主隔膜材質 Material of Main Diaphragm			推薦規格 Recommended Specifications
			鋁 (AL)	不銹鋼 (SUS316)	聚丙烯 (PP)	超高分子聚乙烯 (UPE)	鐵氟龍 (Teflon)	熱塑性橡膠 (Santoprene)	
644	Aluminium chlorate (aqueous)	氯酸鋁(含水)				A			
645	Barium chlorate	氯酸鋇		A			A 20°C		DSXX-SAX-TSXS-XX
646	Barium chloride (dry)	氯酸鋇 (乾)		A			A		DSXX-SAX-TSXS-XX
647	Barium chloride (wet)	氯酸鋇 (濕)		C	A	A	A		DSXX-PXX-TPTP-XX
648	Chlorosulfonic acid	氯磺酸	C	B	D	C	A 20°C	A	DSXX-SAX-OSXS-XX
649	Mercuric cyanide	氰化汞	D	C	A		A	A	DSXX-PXX-TPTP-XX
650	Copper cyanide	氰化亞銅			A	A		A	DSXX-PXX-OTPT-XX
651	Sodium cyanide	氰化鈉	C	B	A	A 30%		A	DSXX-PXX-OTPT-XX
652	Potassium cyanide	氰化鉀	D	B	A	A	A	A	DSXX-PPX-TPTP-XX
653	Turbine Oil	渦輪機油	A	A		A 40°C	A		DSXX-AAX-UEXS-XX
654	Wool oil (Wool grease)	無水羊毛脂			B		A		DSXX-PXX-TPTP-XX
655	Sodium pyrosulfite	焦亞硫酸鈉				A			
656	Tar acid	焦油酸					A 20°C		
657	Disulfuric acid	焦硫酸					A		
658	Cokes oven gas	焦爐煤氣					A	B	
659	Oleum (Sulfuric acid-fuming)	發煙硫酸	B	B	C		A 20°C		DSXX-SAX-TSXS-XX
660	Nitroethane	硝基乙烷	A	A	C		A	A	DSXX-AAX-TAXS-XX
661	Nitropropane	硝基丙烷	A			A 20°C	A		DSXX-AAX-UXTX-XX
662	Nitrotoluene	硝基甲苯		B		A 20°C	A		DSXX-SAX-TSXS-XX
663	Nitromethane	硝基甲烷	A	A	B		A	A	DSXX-AAX-TAXS-XX
664	Nitrobenzene	硝基苯	A	A	B		A 20°C	B	DSXX-AAX-TAXS-XX
665	Nitric acid (<20%)	硝酸 (<20%)	C	A	A	A	A	C	DSXX-PXX-TPTP-XX
666	Nitric acid (>86%)	硝酸 (>86%)	C	A	C	A	A	D	DSXX-SAX-TSXS-XX
667	Nitric acid (40-60%)	硝酸 (40-60%)	C	A	C	A	A	D	DSXX-SAX-TSXS-XX
668	Nitric acid 100%	硝酸 100%	C	B	C	A	A	D	DSXX-SAX-TSXS-XX
669	Nitric acid 25%	硝酸 25%	C	A	B	A	A	C	DSXX-SAX-TSXS-XX
670	Mercurous nitrate	硝酸亞汞		B			A		DSXX-SAX-TSXS-XX
671	Sodium nitrate	硝酸鈉	A	A	A	A	A 60°C	A	DSXX-AAX-UEXS-XX
672	Calcium nitrate	硝酸鈣	A	B	A	A	A	A	DSXX-AAX-OXXX-XX
673	Potassium nitrate	硝酸鉀			A	A	A		DSXX-PXX-TPTP-XX

A = Excellent

B = Good Minor, Effect, slight corrosion or discoloration.

C = Fair Moderate/Effect, not recommended for continuous use. Softening, loss of strength, swelling may occur.

D = Severe Effect, not recommended for ANY use.

No.	English Name	Chinese Name	接液部材質 Material of Wetted Body			主隔膜材質 Material of Main Diaphragm			推薦規格 Recommended Specifications
			鋁 (AL)	不銹鋼 (SUS316)	聚丙烯 (PP)	超高分子聚乙烯 (UPE)	鐵氟龍 (Teflon)	熱塑性橡膠 (Santoprene)	
674	Lead nitrate	硝酸鉛	D	B	A		A		DSXX-PXX-TPTP-XX
675	Silver nitrate	硝酸銀	D	A	A		A 20°C	A	DSXX-PXX-TPTP-XX
676	Copper nitrate	硝酸銅		A			A		DSXX-SAX-TSXS-XX
677	Ammonium nitrate	硝酸銨		A	A	A	A	A	DSXX-PXX-OPTP-XX
678	Aluminium nitrate (aqueous)	硝酸鋁(含水)	A	A	A	A	A	A	DSXX-PXX-OPTP-XX
679	Strontium nitrate	硝酸銣		B					
680	Magnesium nitrate	硝酸鎂	B	A	A		A	A	DSXX-PXX-OPTP-XX
681	Ferric nitrate	硝酸鐵		B			A	A	DSXX-SAX-OSXS-XX
682	Stearic acid	硬脂酸					A	B	
683	Butyl stearate	硬脂酸丁酯	A		A		A	C	DSXX-AAX-TAXS-XX
684	Rape oil	菜籽油		A			A	B	DSXX-SAX-TSXS-XX
685	Naphtalene	萘	A	A		A	A 20°C	C	DSXX-AAX-UEXS-XX
686	Naphthoic acid	萘甲酸					A		
687	Calcium phosphor fluoride	鈣黃磷氟化物					A		
688	Maleic acid	順丁烯二酸			A	A	A 20°C		DSXX-PXX-TPTP-XX
689	Maleic anhydride	順丁烯二酸酐	A	A			A	A	DSXX-AAX-TAXS-XX
690	Drinking water	飲用水	C	A	B		A	A	DSXX-SAX-TSXS-XX
691	Dimethyl propane	新戊烷					A		
692	Coconut fat	椰子油脂	B	A	A		A		DSXX-PXX-TPTP-XX
693	Bromine (dry)	溴(乾)	B	D	D		A	C	DSXX-AAX-TSXS-XX
694	Bromine (wet)	溴(濕)	D	D	D		A	B	
695	Butyl bromide	溴丁烷					A		
696	Hydrogen bromide	溴化氫	C	C	A	C	A		DSXX-PXX-TPTP-XX
697	Sodium bromide	溴化鈉	D	C			A		
698	Calcium bromide	溴化鈣		C					
699	Potassium bromide	溴化鉀	C	B	A		A	A	DSXX-PPX-TPTP-XX
700	Ammonium bromide	溴化銨	D	C		A			
701	Aluminium bromide	溴化鋁				A			
702	Methyl bromide	溴甲烷	D	A	D		A	D	DSXX-SAX-TSXS-XX
703	Monobromobenzene (Bromine benzol)	溴苯			C	C	A	D	

A = Excellent

B = Good Minor, Effect, slight corrosion or discoloration.

C = Fair Moderate/Effect, not recommended for continuous use. Softening, loss of strength, swelling may occur.

D = Severe Effect, not recommended for ANY use.

No.	English Name	Chinese Name	接液部材質 Material of Wetted Body			主隔膜材質 Material of Main Diaphragm			推薦規格 Recommended Specifications
			鋁 (AL)	不銹鋼 (SUS316)	聚丙烯 (PP)	超高分子聚乙烯 (UPE)	鐵氟龍 (Teflon)	熱塑性橡膠 (Santoprene)	
704	Bromic acid	溴酸		C			A	B	
705	Potassium bromate	溴酸鉀		B		A 10%	A		DSXX-SAX-TSXS-02
706	Solvent Naphtha	溶劑石油腦				A	A		
707	Talc	滑石	A		A		A 20°C		DSXX-AAX-TAXS-XX
708	Kerosine	煤油	A	A	C	A	A	C	DSXX-AAX-UEXS-XX
709	Coal tar oil	煤焦油				A			
710	Borax (Sodium tetraborate)	硼砂 (四硼酸鈉)	A	A	A	A	A	A	DSXX-PXX-OPTP-XX
711	Boric acid	硼酸	A	A	A	A	A 60°C	A	DSXX-PXX-OPTP-XX
712	Amyl borate	硼酸戊酯					A	B	
713	Potassium borate	硼酸鉀			A		A		DSXX-PXX-TPTP-XX
714	Iodine	碘	A	D	A		A	A	DSXX-AAX-TAXS-XX
715	Sodium iodide	碘化鈉		B			A		DSXX-SAX-TXTS-XX
716	Potassium iodide	碘化鉀	B	B	A	A	A		DSXX-PAX-TPTX-XX
717	Tincture iodine	碘酊					A		
718	Carboxylic acid	羧酸					A 60°C	C	
719	Glucose (Corn Syrup)	葡萄糖	A	A	A	A	A	A	DSXX-PXX-OPTP-XX
720	Pinene	蒎烯	A				A	C	DSXX-AAX-TAXS-XX
721	Persulfuric acid	過氧—硫酸					A		
722	Benzoyl peroxide	過氧化苯甲醯					A 60°C		
723	Hydrogen peroxide	過氧化氫(雙氧水)	A	B	A	A	A		DSXX-AAX-UEXS-XX
724	Sodium peroxide	過氧化鈉	A	A	A		A 20°C	B	DSXX-AAX-TAXS-XX
725	Potassium persulfate	過硫酸鉀				A			
726	Ammonium persulfate	過硫酸銨	C	B	A	A			DSXX-PXX-TPTP-XX
727	Potassium perchlorate(aqueous)	過氯酸鉀 (含水)				A	A		
728	Sodium perborate	過硼酸鈉	A		A	A	A	A	DSXX-AAX-UEXS-XX
729	Potassium permanganate	過錳酸鉀	B	B	A		A	A	DSXX-PXX-TPTP-XX
730	Casein - 65°C	酪蛋白 - 65°C	B	B			A		DSXX-SAX-TSXS-XX
731	Ketones	酮	B	A			A	C	DSXX-SAX-TSXS-XX
732	Esters, aliphatic	酯類 · 脂肪		A			A		DSXX-SAX-TSXS-XX
733	Cobalt salt	鈷鹽				A			

A = Excellent B = Good Minor, Effect, slight corrosion or discoloration. C = Fair Moderate/Effect, not recommended for continuous use. Softening, loss of strength, swelling may occur. D = Severe Effect, not recommended for ANY use.									
No.	English Name	Chinese Name	接液部材質 Material of Wetted Body			主隔膜材質 Material of Main Diaphragm			推薦規格 Recommended Specifications
			鋁 (AL)	不銹鋼 (SUS316)	聚丙烯 (PP)	超高分子聚乙烯 (UPE)	鐵氟龍 (Teflon)	熱塑性橡膠 (Santoprene)	
734	Potassium nitric acid	鉀硝酸					A		
735	Battery acid	電酸	C		A		A		DSXX-PXX-TPTP-XX
736	Hydroquinone	對苯二酚	A	A		A	A	A	DSXX-AAX-UEXS-XX
737	Carbon oxide (wet)	碳氧化物 (濕)		A	A		A	A	DSXX-PXX-OTPT-XX
738	Carbonic acid gas	碳酸氣			A	A	A	A	DSXX-PXX-OTPT-XX
739	Bicarbonate of soda(Sodium bicarbonate)	碳酸氫鈉	B	A	A		A	A	DSXX-PAX-TPTP-XX
740	Potassium bicarbonate	碳酸氫鉀	B	A	A		A	A	DSXX-PXX-TPTP-XX
741	Sodium carbonate	碳酸鈉	D	A	A		A		DSXX-PXX-TPTP-XX
742	Calcium carbonate	碳酸鈣	A		A			A	DSXX-AAX-OXXX-XX
743	Carbonated beverages	碳酸飲料		A			A	A	DSXX-SAX-TSXS-XX
744	Potassium carbonate	碳酸鉀		A	A	A	A 40°C		DSXX-PXX-TPTP-XX
745	Ammonium carbonate	碳酸銨			A		A	A	DSXX-PXX-OTPT-XX
746	Barium carbonate	碳酸鋇	D	B	A		A	A	DSXX-PPX-TPTP-XX
747	Magnesium carbonate	碳酸鎂	A	B	A		A	A	DSXX-AAX-TAXS-XX
748	Essential oils	精油		A			A		DSXX-SAX-TSXS-XX
749	Refined petroleum	精煉石油		A			A		DSXX-SAX-TSXS-XX
750	Polyoxymethylene	聚甲醛					A		
751	Terpineol	萜品醇	A	A	D		A	B	DSXX-AAX-TAXS-XX
752	Terpene hydrocarbon	萜烯烴					A		
753	Steam	蒸汽		A	B		A		DSXX-SAX-TSXS-XX
754	Anthracene	蒽 (綠油腦)		A			A		DSXX-SAX-TSXS-XX
755	Castoroil	蓖麻油		A			A		DSXX-SAX-TSXS-XX
756	Yeast	酵母		B	A		A 20°C		DSXX-PXX-TPTP-XX
757	Chromic acid(Under 50%)	鉻酸 (50%以內)	C	B	A	A	A		DSXX-PXX-TPTP-XX
758	Sodium chromate	鉻酸鈉		A				A	DSXX-SAX-OSXS-XX
759	Potassium chromate	鉻酸鉀			A		A	A	DSXX-PXX-OTPT-XX
760	Chromium salt	鉻鹽				A			
761	Copper vitriol	銅礬	C		A		A		DSXX-PXX-TPTP-XX
762	Jet fuel	噴射燃料	A	A		A	A	C	DSXX-AAX-UEXS-XX

A = Excellent

B = Good Minor, Effect, slight corrosion or discoloration.

C = Fair Moderate/Effect, not recommended for continuous use. Softening, loss of strength, swelling may occur.

D = Severe Effect, not recommended for ANY use.

No.	English Name	Chinese Name	接液部材質 Material of Wetted Body			主隔膜材質 Material of Main Diaphragm			推薦規格 Recommended Specifications
			鋁 (AL)	不銹鋼 (SUS316)	聚丙烯 (PP)	超高分子聚乙烯 (UPE)	鐵氟龍 (Teflon)	熱塑性橡膠 (Santoprene)	
763	Inks	墨水	A	A	A	A	A	C	DSXX-AAX-UEXS-XX
764	Camphor oil	樟腦油		A			A		DSXX-SAX-TSXS-XX
765	Lubricating oil	潤滑油	A	A	A	A	A	D	DSXX-AAX-UEXS-XX
766	Glue	膠水	A	A	A	A	A	A	DSXX-AAX-TAXS-XX
767	Cane sugar juices	蔗糖汁		A	A		A	A	DSXX-SAX-TSXS-XX
768	Cane sugar syrup	蔗糖糖漿		A	A		A		DSXX-SAX-TSXS-XX
769	Oils, vegetable	蔬菜油	A	A	B		A		DSXX-SAX-TSXS-XX
770	Lard	豬油		A	A		A	B	DSXX-SAX-TSXS-XX
771	o-Xylene/ p-Xylene	鄰二甲苯 / 對二甲苯		A			A		DSXX-SAX-TSXS-XX
772	Dichlorobenzene	鄰二氯苯	D	B	C		A	D	DSXX-SAX-TSXS-XX
773	Chresylic acid	鄰甲酚					A	B	
774	Phthalicacid	鄰苯二甲酸		B		A 50%	A 20°C		DSXX-SAX-TSXS-XX
775	Diethyl phthalate	鄰苯二甲酸二乙酯	A	A		A	A		DSXX-AAX-UEXS-XX
776	Dibutyl Phthalate (DBP)	鄰苯二甲酸二丁酯	A	A	D	A	250°C	D	DSXX-AAX-UEXS-XX
777	Dihexyphthalate	鄰苯二甲酸二己酯				A			
778	Dimethyl phthalate	鄰苯二甲酸二甲酯	A				A	A	DSXX-AAX-TAXS-XX
779	Dioctyl phthalate	鄰苯二甲酸二辛酯	A		B	A	A	C	DSXX-AAX-UEXS-XX
780	Diisobutyl phthalate	鄰苯二甲酸二異丁酯					A		
781	Diisodecyl phthalate	鄰苯二甲酸二癸酯					A		
782	Phthalicacid anhydride	鄰苯二甲酸酐			A	A	A		DSXX-PXX-TPTP-XX
783	Vinegar	醋		A	A	A	A 20°C	A	DSXX-PXX-OPTP-XX
784	Copper acetoarsenite	醋酸亞砷酸銅					A		
785	Lead acetate	醋酸鉛			A	A	A 20°C	A	DSXX-PXX-OPTP-XX
786	Aldehydes	醛					A		
787	Aluminium fluoride 65° C	鋁氟化物 (65°C)	B	C	A		A		DSXX-PXX-TPTP-XX
788	Sodium aluminate	鋁酸鈉		B		A	A	A	DSXX-SAX-USXS-XX
789	Glutamicacid	麩胺酸		B			A		DSXX-SAX-TSXS-XX
790	Gear oil	齒輪油	A	A			A		DSXX-AAX-TAXS-XX
791	Thiophene	噻吩		A		A	A		DSXX-SAX-USXS-XX
792	Resinic acids	樹脂酸					A		

A = Excellent

B = Good Minor, Effect, slight corrosion or discoloration.

C = Fair Moderate/Effect, not recommended for continuous use. Softening, loss of strength, swelling may occur.

D = Severe Effect, not recommended for ANY use.

No.	English Name	Chinese Name	接液部材質 Material of Wetted Body			主隔膜材質 Material of Main Diaphragm			推薦規格 Recommended Specifications
			鋁 (AL)	不銹鋼 (SUS316)	聚丙烯 (PP)	超高分子聚乙烯 (UPE)	鐵氟龍 (Teflon)	熱塑性橡膠 (Santoprene)	
793	Olive oil	橄欖油	A	A	A		A	B	DSXX-SAX-TSXS-XX
794	Motor oil	機油	A	A	B		A		DSXX-AAX-UEXS-XX
795	Starch	澱粉		A	B		A 20°C	A	DSXX-SAX-OSXS-XX
796	Fuel oil	燃料油	A	A	C		A	C	DSXX-AAX-TAXS-XX
797	Lamp oil	燈油		A			A		DSXX-SAX-TSXS-XX
798	Sugar solutions	糖溶液	A	A	A	A	A	A	DSXX-SAX-TSXS-XX
799	Molasses	糖蜜	A	A	A		A		DSXX-AAX-TAXS-XX
800	Cyclohexanone	環乙酮	A		A	A	A 20°C	C	DSXX-PXX-TPTP-XX
801	Cyclohexanol	環乙醇			A	A	A	B	DSXX-PXX-TPTP-XX
802	Cyclohexatriene	環己三烯					A		
803	Cyclohexylamine	環己胺				A	A	B	
804	Cyclohexane	環己烷		B	A	A	A	C	DSXX-PXX-TPTP-XX
805	Hexahydrophenol	環己醇(六氫苯酚)					A		
806	Cyclopentane	環戊烷	B	B			A		DSXX-AAX-TAXS-XX
807	Ethylene oxide	環氧乙烷		B			A		DSXX-SAX-TSXS-XX
808	Propylene oxide	環氧丙烷			A	A	A	A	DSXX-PXX-OTPT-XX
809	Epichlorohydrine (dry)	環氧氯丙烷 (乾)		A					
810	Epichlorohydrine (wet)	環氧氯丙烷 (濕)		C		A	A	B	
811	Phosphoric acid	磷酸	C	B	A	A	A	C	DSXX-PXX-TPTP-XX
812	Phosphoric acid 10%	磷酸 10%	C	B	A	A	A	A	DSXX-PXX-OTPT-XX
813	Tributoxyethyl phosphate	磷酸三丁氧基乙酯					A		
814	Tributyl phosphate	磷酸三正丁酯	A	A	B	A	A	B	DSXX-AAX-UEXS-XX
815	Tricresyl phosphate	磷酸三甲苯酯	C		A		A	B	DSXX-PXX-TPTP-XX
816	Trioctyl phosphate	磷酸三辛酯			A	A	A		DSXX-PXX-TPTP-XX
817	Sodium Phosphate	磷酸鈉	C	A	A			A	DSXX-PXX-OTPT-XX
818	Calcium phosphate	磷酸鈣	D			A			
819	Cellulube® Hydraulic Fluids (Phosphate Esters)	磷酸酯	A	A			A	D	DSXX-AAX-TAXS-XX
820	Potassium phosphate	磷酸鉀	D	B			A		DSXX-SAX-TSXS-XX
821	Ammonium diphosphate	磷酸銨			A	A			DSXX-PXX-TPTP-XX

A = Excellent

B = Good Minor, Effect, slight corrosion or discoloration.

C = Fair Moderate/Effect, not recommended for continuous use. Softening, loss of strength, swelling may occur.

D = Severe Effect, not recommended for ANY use.

No.	English Name	Chinese Name	接液部材質 Material of Wetted Body			主隔膜材質 Material of Main Diaphragm			推薦規格 Recommended Specifications
			鋁 (AL)	不銹鋼 (SUS316)	聚丙烯 (PP)	超高分子聚乙烯 (UPE)	鐵氟龍 (Teflon)	熱塑性橡膠 (Santoprene)	
822	Aluminium phosphate (aqueous)	磷酸鋁(含水)		A	A	A	A		DSXX-PXX-TPTP-XX
823	Furfuryl alcohol	糠醇	A	A		A 50°C	A	B	DSXX-AAX-UEXS-XX
824	Furfural (Ant Oil)	糠醛	A	A	D	A		C	DSXX-AAX-UEXS-XX
825	Biphenyl (Diphenyl)	聯苯	A				A		DSXX-AAX-TAXS-XX
826	Hydrazine (Diamine)	聯氨	A	A	D	A	A 20°C	A	DSXX-AAX-UEXS-XX
827	Menthol	薄荷腦		A	A		A		DSXX-PXX-TPTP-XX
828	Ether	醚		A	C		A 20°C		DSXX-SAX-TSXS-XX
829	Magnesium lye	鎂灰汁				A			
830	Dipentene	檸檬烯	A	A			A	C	DSXX-AAX-TAXS-XX
831	Limonene	檸檬油精		A			A		DSXX-SAX-TSXS-XX
832	Citric acid	檸檬酸		B	B	A	A	A	DSXX-PXX-OPTP-XX
833	Sodium citrate	檸檬酸鈉	D	B					
834	Epsom salt	瀉鹽	A	A		A	A	A	DSXX-AAX-UEXS-XX
835	Lavender oil	薰衣草油		A			A	B	DSXX-SAX-TSXS-XX
836	Nickel salt	鎳鹽					A 20°C		
837	Dichloroethyl ether	雙(氯乙基)醚	B				A		DSXX-AAX-TAXS-XX
838	Diacetone alcohol	雙丙酮醇	A			A	A	B	DSXX-AAX-UEXS-XX
839	Diisopropylidene acetone	雙異丙叉丙酮					A	B	
840	Dicyclopentadiene	雙環戊二烯					A	C	
841	Creosote (wood)	雜酚油(木頭)		A			A		DSXX-SAX-TSXS-XX
842	Creosote tar (coal tar)	雜酚油(煤焦油)	A	A	A		A		DSXX-AAX-TAXS-XX
843	Tannic acid	鞣酸					A 20°C	A	
844	Asphalt (Bitumen)	瀝青	A	A	A		A	B	DSXX-AAX-TAXS-XX
845	Mineral Oil (Petroleum)	礦物油	A	A	A	A	A	C	DSXX-AAX-UEXS-XX
846	Mineral jelly	礦物凍		A			A		DSXX-SAX-TSXS-XX
847	Mineral motorfuels	礦物發動機燃料		A			A		DSXX-SAX-TSXS-XX
848	Mineral water	礦泉水	A	A	A		A		DSXX-PXX-TPTP-XX
849	Vitriol oil	礬油		A	A				DSXX-PXX-TPTP-XX
850	Cider	蘋果汁	C	A	A			D	DSXX-SAX-TSXS-XX
851	Malic acid	蘋果酸			A	A	A	A	DSXX-PXX-OPTP-XX

A = Excellent

B = Good Minor, Effect, slight corrosion or discoloration.

C = Fair Moderate/Effect, not recommended for continuous use. Softening, loss of strength, swelling may occur.

D = Severe Effect, not recommended for ANY use.

No.	English Name	Chinese Name	接液部材質 Material of Wetted Body			主隔膜材質 Material of Main Diaphragm			推薦規格 Recommended Specifications
			鋁 (AL)	不銹鋼 (SUS316)	聚丙烯 (PP)	超高分子聚乙烯 (UPE)	鐵氟龍 (Teflon)	熱塑性橡膠 (Santoprene)	
852	Rum	蘭姆酒		A			A	A	DSXX-SAX-TSXS-XX
853	Potassium ferricyanide	鐵氰化鉀	B	B	A		A 100°C	A	DSXX-PXX-TPTP-XX
854	Methylated spirit	變性乙醇	A		A		A		DSXX-AAX-TAXS-XX
855	Transformer oil	變壓器油	A	A	A	A	A	D	DSXX-AAX-UEXS-XX
856	Developer	顯影劑			A		A	A	DSXX-PXX-TPTP-XX
857	Bismuth carbonate	鹼式碳酸鉍		B			A		DSXX-SAX-TSXS-XX
858	Salt solutions (Brine)	鹽水	C	C	A		A	A	DSXX-PXX-OPTP-XX
859	Hydrochloric acid (Under 20%)	鹽酸 (20%以內)	D	C	A	A	A	A	DSXX-PXX-TPTP-XX
860	Hydrochloric acid 38%	鹽酸 (20-50%)	D	D	A	A	A		DSXX-PXX-TPTP-XX
861	Hydrochloric acid 100%	鹽酸 100%	D	D	A	A	A		DSXX-PXX-TPTP-XX